

Alloy 5456

Chemical Composition Limits

ELEMENT

WEIGHT %	Cu	Mg	Mn	Si	Fe	Zn	Ti	Cr	Each	Total
MINIMUM	-	4.70	0.50	-	-	-	-	0.05	-	-
MAXIMUM	0.10	5.50	1.00	0.25	0.40	0.25	0.20	0.20	0.05	0.15

Typical Physical Properties

	AVERAGE COEFFICIENT OF THERMAL EXPANSION	MELTING RANGE APPROX.	TEMPER	THERMAL CONDUCTIVITY AT 77°F	ELECTRICAL CONDUCTIVITY AT 68°F		ELECTRICAL RESISTIVITY AT 68°F
	(68-212°F PER F)	°F		ENGLISH UNITS	EQUAL VOLUME	EQUAL WEIGHT	OHM-CIR. MIL/FOOT
ALLOY 5456	13.3	1055-1180	O	810	29	98	36

Typical US Mechanical Properties

ALLOY AND TEMPER	TENSION				HARDNESS	SHEAR	FATIGUE	MODULUS
	STRENGTH KSI		ELONGATION PERCENT IN 2 IN.		BRINNELL NUMBER	ULTIMATE SHEARING STRENGTH	ENDURANCE LIMIT	MODULUS OF ELASTICITY
	ULTIMATE	YIELD	1/16 IN. THICK SPECIMEN	1/2 IN. DIAMETER SPECIMEN	500 KG LOAD 10 MM BALL	KSI	KSI	KSI X 10 ³
5456-O	45	23	-	24	-	-	-	10.3
5456-H25	45	24	-	22	-	-	-	10.3
5456-H116	51	37	-	16	90	30	-	10.3
5456-H321	51	37	-	16	90	30	-	10.3

The following typical properties are not guaranteed, since in most cases they are averages for various sizes, product forms and methods of manufacture and may not be exactly representative of any particular product or size. This data is intended only as a basis for comparing alloys and tempers and should not be specified as engineering requirements or used for design purposes.

